



EIGER OFFSET

Basis weight, g/m2 (ISO 536)	CIE Whiteness, % (ISO 11475)	Opacity, % (ISO 2471)	Roughness, ml/min (ISO 8791-2)	Bulk, cm3/g (ISO 534)
70	163	91	145	1.31
80	163	94	145	1.28
90	163	95	145	1.29
100	163	96	145	1.28
110	163	97	145	1.28
120	163	98	145	1.25

NB - 60gsm and 75gsm are available upon request

The figures shown in the table are based on average values



Eiger Offset is produced as 70% PEFC certified as standard
Eiger Offset is also available on request as FSC® Mix 70%, subject to availability

Brunswick House, Regent Park
297-299 Kingston House, Leatherhead
Surrey KT22 7LU
t. +44 (0) 1372 385101
f: +44 (0) 1372 386366
e: sales@gouldinternational.co.uk
w. www.gouldpublicationpapers.co.uk